



**SUPERALLOYS**

**ORIC ITALIANA S.R.L.**

*Indirizzo: Via dell' Industria, 4 - Zona Industriale*

*Località: Castel San Giovanni 29015 (PC) Italy*

*Tel: +039 0523 882498*

*Fax: +039 0523 883111*

*Email: [info@oric.it](mailto:info@oric.it)*

## *Tabella Carburo di Tungsteno*

CARBURO DI TUNGSTENO	SPECIFICHE				ANALISI		
	ISO	Hardness		Density	W	Co	Others
		HV	HRA	Kg/dm <sup>3</sup>	%	%	%
ST 01	K01	1800	93	15,05	BAL	4,5	3
ST 10	K10	1700	92,5	14,95	BAL	5,5	0,5
ST 15	K15	1600	91,8	14,45	BAL	10	0,5
ST 20	K20	1580	91,6	14,85	BAL	6,5	0,5
ST 30	K30	1450	90,7	14,65	BAL	8,5	0,5
ST 40	K40	1295	89,5	14,3	BAL	12	1
ST 11 Co	SPEC	1270	89,2	14,4	BAL	11	
ST 45	K45	1210	88,4	14,05	BAL	15	0,55
ST 50	K50	1100	87	14	BAL	15	0,5
STG 30	G30	1070	86,7	14,05	BAL	15	
ST 17 Co	SPEC	1040	86,3	13,8	BAL	17,5	
STG 40	G40	910	84,8	13,6	BAL	20	
STG 50	G50	810	83,2	13,1	BAL	25	
ST 37	SPEC	1370	90,2	14,06	BAL	---	8,5 Nickel