



SUPERALLOYS

ORIC ITALIANA S.R.L.

Indirizzo: Via dell' Industria, 4 - Zona Industriale

Località: Castel San Giovanni 29015 (PC) Italy

Tel: +039 0523 882498

Fax: +039 0523 883111

Email: info@oric.it

Tabella Cobalto

COBALTO	SPECIFICHE					ANALISI					
	Grado	ASTM	AMS	Durezza	Densità	Co	C	Cr	Ni	Mo	W
				HRc	Kg/dm ³	%	%	%	%	%	%
371	1	CoCr-C		51 - 57	8,69	BAL	2,5	33			13
373	3			51 - 55	8,69	BAL	2,3	30			13
384	4			45 - 49	8,73	BAL	1	32			14
386	6	CoCr-A	5373 / 5387	38 - 42	8,46	BAL	1	26			4
372	12	CoCr-B		47 - 51	8,56	BAL	1,8	29			9
370	20			54 - 59	8,8	BAL	2,5	33			18
388	21		5385	30 - 37	8,34	BAL	0,3	28	2	5,5	
382	25			21 - 30	8,05	BAL	0,4	18	10		15
400	100			57 - 62	8,75	BAL	2	34			19
377	F			40 - 46	8,6	BAL	1,6	25	22		12