



SUPERALLOYS

ORIC ITALIANA S.R.L.

Indirizzo: Via dell' Industria, 4 - Zona Industriale

Località: Castel San Giovanni 29015 (PC) Italy

Tel: +039 0523 882498

Fax: +039 0523 883111

Email: info@oric.it

Tabella Saldatura Cobalto

COBALTO	SPECIFICHE				ANALISI					
	Grado	AWS	AMS	Durezza	Co	C	Cr	Ni	Mo	W
				HRc	%	%	%	%	%	%
371	1	CoCr-C		51 – 57	BAL	2,5	33			13
373	3			51 – 55	BAL	2,3	30			13
384	4			45 – 49	BAL	1	32			14
386	6	CoCr-A	5373 / 5387	38 – 42	BAL	1	26			4
372	12	CoCr-B		47 – 51	BAL	1,8	29			9
370	20			54 – 59	BAL	2,5	33			18
388	21		5385	30 – 37	BAL	0,3	28	2	5,5	
382	25			21 – 30	BAL	0,4	18	10		15
400	100			57 – 62	BAL	2	34			19
377	F			40 – 46	BAL	1,6	25	22		12